




SiSiB[®] PC9540 SILANE

- 1 -

CHEMICAL NAME

Isobutylisopropyldimethoxysilane

CHEMICAL STRUCTURE



INTRODUCTION

SiSiB[®] PC9540 is used in combination with Ziegler-Natta catalysts to increase the isotactic index of Polypropylene.

TYPICAL PHYSICAL PROPERTIES

CAS No.	111439-76-0
ELINCS No.	402-580-4
Formula	C ₉ H ₂₂ O ₂ Si
Molecular Weight	190.36
Boiling Point	178°C [760mmHg]
Flash Point	49°C
Appearance	Colorless clear liquid
Density _{25/25°C}	0.87
Refractive Index	1.4125 [20°C]
Purity:	Min 99.0%
Methanol Content	0.1% wt max.
Hydrolyzable Chloride	0.001% wt max.

APPLICATIONS

SiSiB[®] PC9540 is used in combination with Ziegler-Natta catalysts to increase the

Power Chemical
ISO9001 ISO14001 certified

Copyright© 2009 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] PC9540 SILANE

- 2 -

isotactic index of Polypropylene.

SiSiB[®] PC9540 can increase yield of polymer per unit weight of catalyst.

SiSiB[®] PC9540 can increase isotactic content of polypropylene-based polymers.

SiSiB[®] PC9540 can improve molecular weight dispersity of the polymer.

OTHER OLEFIN POLYMERIZATION CATALYSTS

SiSiB [®] PC5410:	Tetramethoxysilane
SiSiB [®] PC5420:	Tetraethoxysilane
SiSiB [®] PC5931:	Trimethoxypropylsilane
SiSiB [®] PC5932:	n-Propyltriethoxysilane
SiSiB [®] PC5951:	Isobutyltrimethoxysilane
SiSiB [®] PC5952:	Isobutyltriethoxysilane
SiSiB [®] PC8132:	Phenyltriethoxysilane (A donor)
SiSiB [®] PC8221:	Dimethoxydiphenylsilane (B donor)
SiSiB [®] PC9500:	Cyclohexyldimethoxymethylsilane (C donor)
SiSiB [®] PC9510:	Diisobutyldimethoxysilane (DIB donor)
SiSiB [®] PC9520:	Diisopropyldimethoxysilane (DIP donor)
SiSiB [®] PC9530:	Dicyclopentyldimethoxysilane (D donor)
SiSiB [®] PC9540:	Isobutylisopropyldimethoxysilane
SiSiB [®] PC9550:	Isobutyldimethoxymethylsilane

PACKING AND STORAGE

SiSiB[®] PC9540 is supplied in net weight 170Kg steel drum or 850Kg IBC container.

In the unopened original container SiSiB[®] PC9540 has a shelf life of one year in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

Power Chemical
ISO9001 ISO14001 certified

Copyright© 2009 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] PC9540 SILANE

- 3 -

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.

Power Chemical
ISO9001 ISO14001 certificated

Copyright© 2009 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia