



# SiSiB® HR6253 HCE

- 1 -

## INTRODUCTION

SiSiB® HR6253 is heat resistant products, can be used below 315°C.

## KEY FEATURES

Excellent processability.

Excellent heat resistant capability

Excellent physical properties

50, 60, 70 durometer grades available

ROHS test passed

## TYPICAL PHYSICAL PROPERTIES

Product	SiSiB® HR6253 HCE
Appearance	Red
Curing Agent	C-15
Curing Agent Content	2.0%
Curing Condition	170°C×10min
Hardness (Shore A)	50+/-3
Tensile Strength (MPa)	Min. 8.0
Elongation (%)	Min. 300
Tensile Set (%)	Max.10.0
Tear Strength (KN/m)	Min. 16.0

## APPLICATIONS

Auto accessories

Wires/Cables/Tubes

Parts

Seals

**Power Chemical**  
ISO9001 ISO14001 certificated

Copyright© 2008 Power Chemical Corporation Ltd.  
SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit [www.SiSiB.com](http://www.SiSiB.com) or [www.PCC.asia](http://www.PCC.asia)



# SiSiB<sup>®</sup> HR6253 HCE

- 2 -

## PACKING AND STORAGE

SiSiB<sup>®</sup> HR6253 is supplied in 20Kg box, with plastic bag inside.

Store in a cool and dry place out of direct sunlight.

## NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: [support@SiSiB.com](mailto:support@SiSiB.com).

**Power Chemical**  
ISO9001 ISO14001 certificated

Copyright© 2008 Power Chemical Corporation Ltd.  
SiSiB<sup>®</sup> is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit [www.SiSiB.com](http://www.SiSiB.com) or [www.PCC.asia](http://www.PCC.asia)